

WEAR SO LApplication Bulletin

Food & Feed Extruder Components

LASTS 4-6x LONGER

For increased service life in the most extreme extrusion processes.

Kennametal Conforma Clad[™] is a leading supplier of extreme wear solutions for applications experiencing severe abrasion, corrosion, and erosion. We manufacture **wear-protected replacement barrels, liners, and screw segments for most 0EMs**.

• Extend Component Life

Superior abrasion and corrosion resistance reduces wear and improves component life 4–6x longer than unprotected equipment.

• Produce Consistent Quality

Protecting critical equipment tolerances permits tighter process control, giving you more consistent product quality and throughput.

Reduce Maintenance Costs & Downtime

Tungsten carbide and Stellite[™] alloy protection greatly increases component life, resulting in fewer rebuilds and less unscheduled downtime.

Lower Cost per Ton

Longer component life, consistent quality, less downtime, and reduced maintenance costs creates a lower production cost per ton.

Full Range of Wear Protection


Kennametal Conforma Clad offers screw segments and liners with a variety of wear protection options. All cladding options fully encapsulate the screw ensuring complete protection.











Stellite and WC Cladding



Full WC Cladding





CA6NM Hardened Stainless

conformaclad.com

WC Cladding and Tiles



Food & Feed Extruder Components

Stellite[™] Cladding

- Maximum corrosion protection for niche pet food formulas.
- Maintains smooth wear surface throughout service life.

Tungsten Carbide Cladding and Solid Carbide Tiles

- Maximum abrasive wear protection.
- Tiles can be applied for enhanced wear properties.

Relative Performance

	Life	Abrasion	Corrosion
CA6NM Hardened Stainless	*	*	*
Full Stellite Cladding	***	***	****
Stellite and WC Cladding	***1	***1	****
Full WC Cladding	***	***	***
WC Cladding and Tiles	****	****	***


Stellite[™] and Conforma Clad[™] are registered trademarks of Kennametal Inc.

Flexible Tungsten Carbide and Stellite Cloth

The Conforma Clad™ process starts with a flexible organic cloth embedded with either tungsten carbide particles or Stellite alloy. This unique cloth technology enables our wear protection to perfectly conform to complex geometries, such as screw surfaces. The infiltration brazing process metallurgically bonds the tungsten carbide or Stellite alloy to the base material. The result is a hard, protective cladding that is extremely durable and wear resistant.

Kennametal Wear-Protected Components

- Single Screws & Liners
- Shear Locks/Lobes
- Sileal Locks/Lobe
- Material Handling
- Twin Extruder Barrels
- Shaft Supports
- Conveyance Piping




Twin Screw Replacement Barrels




Tungsten Carbide and Stellite alloy wear protection applied where you need it most.

Performance Data

WC 219 Cladding Properties				
Total Carbide Loading	62%			
Density (lb/in³)	0.40			
Thermal Conductivity (BTU in/h•ft²•°F)	170			
Metallurgical Bond Strength (psi)	>70,000			
Porosity	<3%			
Rockwell Hardness (HRC)	56–62			





CONTACT US

Order Support: k-nalb.cs@kennametal.com | +1 888 289 4590

Kennametal Conforma Clad 501 Park East Blvd. New Albany, IN 47150 USA

©2019 Kennametal Inc. | All rights reserved. | B-19-05995EN



conformaclad.com