

KGT-50 GRANULATED TUNGSTEN (-12/+40 mesh) MM#6296939

Kennametal Inc.
7300 Highway 20 West | Huntsville, AL 35806 USA
T 888.777.6852
www.kennametal.com
k-hntv.inside-sales@kennametal.com




Properties:

Tungsten*	≥99.7%
Scott Density	100-140 g/in ³
Sintered Density	~17.3 g/cm ³ (90% of Theoretical)
+12mesh	≤2%
12 – 40 mesh	≥95%
-40 mesh	≤5%

*Reduced in a Hydrogen Furnace. Tungsten by difference excluding gasses.

Morphology:



NOTICE: THIS DOCUMENT IS THE PROPERTY OF KENAMETAL INC. AND CONTAINS KENAMETAL PROPRIETARY INFORMATION/TRADE SECRET INFORMATION. IT HAS BEEN SUBMITTED TO YOU IN CONFIDENCE FOR A SPECIFIC PURPOSE. AND DISSEMINATION, DISTRIBUTION, OR DUPLICATION OF THIS COMMUNICATION BY SOMEONE OTHER THAN THE INTENDED RECIPIENT IS STRICTLY PROHIBITED.