

GRANULATED W (-20/+40 mesh)
MM#5871845

Kennametal Inc.
7300 Highway 20 West | Huntsville, AL 35806 USA
T 888.777.6852
www.kennametal.com
k-hntv.inside-sales@kennametal.com




Typical Properties:

Tungsten*	$\geq 99.7\%$
Scott Density	100-140 g/in ³
+20mesh	$\leq 10\%$
20 – 40 mesh	$\geq 90\%$
-40 mesh	$\leq 5\%$

*Reduced in a Hydrogen Furnace. Tungsten by difference excluding gasses.

Morphology:



NOTICE: THIS DOCUMENT IS THE PROPERTY OF KENNAMETAL INC. AND CONTAINS KENNAMETAL PROPRIETARY INFORMATION/TRADE SECRET INFORMATION. IT HAS BEEN SUBMITTED TO YOU IN CONFIDENCE FOR A SPECIFIC PURPOSE. AND DISSEMINATION, DISTRIBUTION, OR DUPLICATION OF THIS COMMUNICATION BY SOMEONE OTHER THAN THE INTENDED RECIPIENT IS STRICTLY PROHIBITED.